

Sayerlack is a brand of
SHERWIN-WILLIAMS

SAYERLACK S.r.l. - With a Single Shareholder

Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18

tel. +39 051 770511 - fax +39 051 777437

www.sayerlack.it - www.lineablavernici.it

Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200

R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Shelf-life:	<p>If the product is properly stored, shelf-life is unlimited.</p> <p>After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.</p>
-------------	--

Technical characteristics of the topcoat TZ22**/13:

Versions	25 and 75 gloss	
Method of use:	spray	
Mixing procedure:	by weight	
Part A	TZ22**/13	100
Part B (hardener)	TH0333/00	50
Solids content (%):	25 gloss	59 ± 2
	75 gloss	64 ± 2
Specific gravity (kg/ltr):	1.150 ± 0.030	
Viscosity (DIN 4 at 20°C):	Part A:	160" ± 10"
	A + B:	20" ± 2"
Drying time:	dust free:	15'
	touch dry:	90'
	stackable:	24 hours
Pot-life:	3 hours	

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Sayerlack is a brand of
SHERWIN-WILLIAMS

SAYERLACK S.r.l. - With a Single Shareholder

Via del Fifico, 12 - 40065 Pianoro (BO) - Italia - C.P. 18

tel. +39 051 770511 - fax +39 051 777437

www.sayerlack.it - www.lineabluevernici.it

Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200

R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 i.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Technical Data Sheet

TB WHITE PU FIRE-RETARDANT SYSTEM

Supersedes previous issue dated 19/12/06

DATE 20/03/08

TB is a code used to encompass the whole fire-retardant coatings system composed of two coats of basecoat (TU0022/13) and one coat of topcoat (TZ2225/13 or TZ2275/13).

It is indispensable to comply with the instructions provided in this technical data sheet to ensure class 1 fire resistance and therefore validity of homologation.

Areas of use

Flat panels (doors), assembled furniture, turned parts.

Not to be used on veneers glued with thermoplastic resins, assembled parts with cellular or laminated structure with air cavities (i.e. rattan) or cavities filled with heterogeneous materials.

Certifications

- UNI 9796 DM 06/03.92 Ministero degli Interni omologazione n° BO1159PVI100002 Cl. 1 di reazione al fuoco.

Description of fire retardant coatings system: (see each component for hardening ratio):

- Basecoat: TU0022/13 (hardener TH0333/00) - 2 coats @ 150 g/m² each (300 g/m² in total)
- Interval between coats: 2 hours

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.