

Technical Data Sheet

DX1131/00
PURE ACETONE

DATE 10/16/00

Technical characteristics:

Specific gravity (kg/l):	0.790 ± 0.030
Flash point:	-17°C
Drying speed (max 100 – min 0):	95
Pot-life extension (max 100 - min 0):	50
Resistivity (Mohm per cm at 20°C):	8
Shelf-life:	If the product is properly stored, shelf-life is unlimited.

General characteristics

DX1131/00 is a thinner suitable for polyester coatings and for stains series XC1900/XX, XM7100/XX, XM8000/XX, XP1950/XX and XP1970/13.

DX1131/00 is pure acetone, practically free from water and other impurities. It is the fastest in our range and, as such, it is particularly suitable for stains to be applied by spray when a very fast drying is required.

It is also suitable for polyester coatings to be applied by spray, since it decreases viscosity and does not remain trapped in the coating film.

For all the other coatings types (nitrocellulose, polyurethanes, etc.), DX1131/00 is too fast a thinner and would cause problems in terms of bad dilatation, whitening in humid weather and pinholes.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.