



Induline 2K Filler

For levelling out uneven areas

Colour	Availability	
	Quantity per pallet	1104
	Packaging unit	500 g
	Container code	01
	Art. no.	
	3261	■

Range of use



- Interior and exterior wood
- Windows, doors, laminated beams, furniture and similar items
- Additional substrates: Sheet steel, cast iron and aluminium, chipboard
- For use by professionals
- Unsuitable substrates:
 - Substrates that can be dissolved by nitrocellulose thinner (e.g. acrylic coatings)
 - Galvanised and hot-dip galvanised sheet metal
 - Reactive primer (wash primer), synthetic resin or nitrocellulose combination primer, because adhesion difficulties are expected on these substrates
 - Tropical woods such as teak and palisander contain substances that can significantly delay or even prevent the hardening of polyester

Property profile



- Elastic, polyester-based 2K fine filler
- Reduced styrene content
- Easy to smooth off
- Good filling capacity
- Easy to sand
- Low volume shrinkage

Possible system products

- [\[remmers_holzinnenlacke_3261\]](#)
- [\[induline_beschichtungssystem_3261\]](#)
- [\[remmers_holzanstriche_fuer_das_handwerk_3261\]](#)

Preparation

- **Substrate requirements**
 The substrate must be clean, dry, capable of bearing a load, and free from substances that may impair adhesion (oil, grease, wax).
 Dimensionally stable wood building elements: wood moisture content 11-15%
 Wood building elements with limited or no dimensional stability: wood moisture content max. 18%

Production of the mixture


- **Mixing**



Thoroughly mix the desired quantity of filler with approx. 2% hardener paste, then apply within 4-5 minutes.

Adding excess hardener paste does not accelerate the polymerisation reaction. In unfavourable conditions, this may even cause colour changes in the subsequent coating.

Directions



Filling

After 20-25 minutes hardening time, Induline 2K filler can be dry-sanded.

Tips on use

When applying filler to exterior wood, swelling and shrinkage of the wood may cause spalling.

Observe BFS Code of Practice No. 18 "Coatings on Wood and Wooden Working Materials in Outdoor Areas".

■ Drying

Practice values at +20 °C and 65% relative humidity.

Notes

Apply to a trial area before use.

Tools / Cleaning



Clean tools using WV-891 Brush Wash or V-890 Thinner.

Any material that has already begun to dry can only be removed mechanically.

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.